





**Mon-Droguiste.Com**  
 39 Bis Rue Du Moulin Rouge  
 10150 Charmont Sous Barbuise  
 Tél : +33.(0)3.25.41.04.05  
 E mail : contact@mon-droguiste  
 Web : www.mon-droguiste.

## DATA SHEET

<b>MINERALOGY [%]</b>	RDA	Talc	
<b>CHEMICAL PROPERTIES [%]</b>	ISO 787/2	Moisture content	≤0,5
		Loss on ignition (1050°C/1h)	12
	Gravimetry	SiO <sub>2</sub>	52,9
	AAS	CaO	2,5
		MgO	31,5
		Al <sub>2</sub> O <sub>3</sub>	0,5
		Fe <sub>2</sub> O <sub>3</sub>	0,7
<b>WHITENESS</b>	Konica Minolta	Y	87
	CM-600d	L*	94,9
	Illuminant D65/10°	a*	-0,2
		b*	1,5
<b>PHYSICAL PROPERTIES</b>	ISO 787/10	Density [g/cm <sup>3</sup> ]	2,78
	EN 1097/3	Loose bulk density [g/cm <sup>3</sup> ]	0,65
	ISO 787/9	pH-value	9,5
	Hardness (Mohs)	Talc	1
	ISO 787/5	Oil absorption [ml/100g]	26
<b>PARTICLE SIZE DISTRIBUTION</b>	Screen residue (Alpine Airjet)	> 63 µm [%]	2
	Master Sizer 2000, HydroG	SediGraph 5100	
	Average particle size D50 [µm]	Average particle size D50 [µm]	10



These data are presented in good faith as typical values for this product. They are not to be considered as binding.

Please bear in mind that our products should be tested for the intended application before use. Users shall be solely and entirely responsible for the intended purpose of application. Please do not hesitate to contact our customer service for any further queries you may have.